

EMERGENCY CONTACTS


Telephone: + 44 (0) 01443 878010

Section 1. Preparation and Company Identification

Product Name **Azo-Cure PF 10-90 Foam**
 Synonyms Polyurethane Foam
 CAS Number Mixture

AZON (UK) LTD.
 Unit J
 St David's Industrial Estate
 Pengam
 Blackwood
 NP12 3SW

Section 2. Hazards Identification

CLP CLASSIFICATION	CLP LABELLING Pictograms; Signal Word Code(s)	Specific Concentration Limits; M-factors
Hazard Class and Category Code(s) Acute Toxicity. 4 (Oral) Hazard Statement Code(s) H302 Harmful if swallowed.	GHS07; Warning 	NONE
P264 Wash ... thoroughly after handling P270 Do not eat, drink or smoke when using this product P330 Rinse mouth. P301 +P312 IF SWALLOWED: Call a POISON CENTER or doctor/physician if you feel unwell P501 Dispose of contents/container properly		

Section 3. Composition / Information on Ingredients**INGREDIENTS**

Ingredient Name	CAS Number	Concentration
Polyether Triol	25791-96-2	<40%
Di(ethylene glycol) phthalate	32472-85-8	<25%
Polyether Polyol Blend	Proprietary	<25%

Section 4. First Aid Measures

First Aid For Eyes- Flush with copious amount of water, preferably lukewarm for at least 15 minutes, holding eyelids open all the time.

First Aid For Skin- Remove contaminated clothing. Wash affected skin thoroughly with soap and water. Wash contaminated clothing thoroughly before reuse.

First Aid For Inhalation- Move to an area free from risk of further exposure.

First Aid For Ingestion- Immediately drink water to dilute. Induce vomiting. Consult physician if symptoms develop. DO NOT GIVE ANYTHING BY MOUTH TO AN UNCONSCIOUS PERSON.

Section 5. Fire Fighting Measures

Flash Point- 150-230 °C

Extinguishing Media- Dry Chemical; Carbon Dioxide; Water spray for large fires.

Special Fire Fighting Instructions- Use water to cool containers. Full emergency equipment with self-contained breathing apparatus and full protective clothing should be worn by firefighters.

Section 6. Accidental Release Measures

Spills Or Leaks Measures- Product is slightly soluble in water. Dike spill area. Absorb with clay, sand, or other commercial absorbant for disposal.

Section 7. Handling and Storage

Storage Temperature- 18 °C / 30 °C; Do not exceed 49 °C.

Special Sensitivity- Opened containers should be protected with a dry air or nitrogen padding. A drierite or silica gel drying system on the vents can also be used.

Section 8. Exposure Controls

Eye Protection Requirements- Safety glasses with sideshields.

Skin Protection Requirement- Not normally required. Chemical resistant gloves recommended.

Ventilation Requirements- Local exhaust ventilation is recommended if vapors, mists, or aerosols are generated. Otherwise, use general exhaust ventilation.

Respirator Requirements- Not normally required.

Section 9. Physical and Chemical Properties

PHYSICAL FORM..... Liquid
COLOR Dark purple to black
ODOR Slight
BOILING POINT 240 °C
SOLUBILITY IN WATER..... Slightly soluble
VAPOR PRESSURE..... <1 m/bar @ 20 °C; 6 m/bar @ 50 °C

Section 10. Stability and Reactivity

Stability- This is a stable material.

Hazardous Polymerization- Will not occur.

Incompatibilities- Strong oxidizers, strong alkalis.

Decomposition Product- Carbon monoxide, carbon dioxide, nitrogen oxides.

Section 11. Toxicological Information

No data is available at this time.

Section 12. Ecological Information

Do not allow material to escape into waters, wastewater or soil.

Section 13. Disposal Considerations

This material it should be disposed of in accordance with local and national regulations. Incineration is the preferred method.

Section 14. Transportation Information

Not regulated for transportation

Section 15. Regulatory Information

Classification and labelling according Regulation on Classification, Labelling and Packaging of Substances and Mixtures (CLP Regulation).

Section 16. Other Information

Reason for issueUpdated Regulatory Information

Prepared bySteve Beck

Approval date.....27-6-2014

WARRANTY The information contained in this document is to assist customers in determining whether our products are suitable for their applications. Our products are intended for sale to industrial and commercial customers. The customer must inspect and test our products before use, and satisfy themselves as to the contents and suitability. Nothing herein shall constitute a warranty, expressed or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent to be inferred. All patent rights are reserved. The exclusive remedy for all proven claims is replacement of our materials, and in no event shall we be liable for special, incidental, or consequential damages.